BAE SECURA PVV BLOCK SOLAR

Technical Specification for Valve Regulated Lead-Acid Batteries (VRLA-GEL)

1. Application

BAE SECURA PVV BLOCK SOLAR batteries are the ideal solution for storage of regenerative energy in home systems and in the industrial sectors. Robustness and reliability are characteristic for BAE SECURA PVV BLOCK Solar batteries. Moreover, they do not require any refilling of water during the whole battery life time and are maintenance-free. The additional option for operation of the batteries in horizontal position allows compact installations especially at home solar systems.

The special electrode design with tubular electrodes and the fixed gel electrolyte distinguish the BAE SECURA PVV BLOCK SOLAR batteries and lead to high security and reliability as well as high cycle life time.



Similar to the illustration


2. Technical data (Reference temperature 20 °C)


Type U _e V/cell	C _{1 h} Ah 1.67	C _{10 h} Ah 1.80	C _{20 h} Ah 1.80	C _{72 h} Ah 1.80	C _{100 h} Ah 1.80	C _{120 h} Ah 1.80	C _{240 h} Ah 1.80	$\begin{array}{c} R_i \\ 1) \\ m\Omega \end{array}$	I _k 2) kA	Length (L) mm	Width (W) mm	Height (H) mm	Weight kg
12 V 1 PVV 70	35	60	67	76	78	79	82	17.47	0.73	272	205	385	43.4
12 V 2 PVV 140	68	110	120	133	137	138	142	9.55	1.34	272	205	385	52.6
12 V 3 PVV 210	103	167	182	203	208	210	216	6.74	1.91	380	205	385	74.8
6 V 4 PVV 280	137	224	244	273	279	282	290	2.66	2.42	272	205	385	50.5
6 V 5 PVV 350	172	281	306	343	350	354	364	2.24	2.87	380	205	385	65.2
6 V 6 PVV 420	207	337	368	412	421	424	439	1.94	3.31	380	205	385	72.5


1, 2) Internal resistance R_i and short circuit current I_k according to IEC 60896-21 Height (H) is the maximum height between container bottom and top of the bolts in assembled condition.

All values published in the table correspond to 100 % discharge of current depending capacity without voltage drop of connectors. Please consider item 7.

3. Terminal positions







6 V 4 PVV 280 to 6 V 6 PVV 420

Terminals are designed as female poles with brass inlay M10 for flexible insulated copper cables with cross-section 25, 35, 50, 70, 95 or 120 mm² or insulated solid copper connectors with cross-section 90, 150 or 300 mm².



Technical Specification for BAE SECURA PVV BLOCK SOLAR









4. Design

Positive electrode Tubular-plate with woven polyester gauntlet and solid grids in a corrosion-resistant

PbCaSn-alloy

Negative electrode Grid-plate in PbCaSn-alloy with long-life expander material

Separation Microporous separator

Electrolyte Sulphuric acid with a density of 1.24 kg/l (20 °C), fixed as GEL by fumed silica Container and lid High impact SAN (Styrene acrylonitrile), grey coloured (colour may vary slightly

from given image), UL-94 rating: HB, on request also in UL-94 rating: V-0

Valve Valve with flame arrestor, opening pressure approx. 120 mbar
Pole-bushing 100 % gas- and electrolyte-tight, sliding, plastic-coated "Panzerpol"
Kind of protection IP 25 regarding EN 60529, touch protected according to BGV A3

Horizontal operation Please use BAE special type PVV "horizontal".

5. Installation

BAE Secura PVV BLOCK Solar batteries are designed for indoor applications.

For outdoor applications please contact BAE.

6. Maintenance

Every 6 months Check battery voltage, pilot block voltages, temperatures

Every 12 months Check connections, record battery voltage, block voltages and temperatures

7. Operational data

Depth of discharge (DOD) Max. 80 % (U_a = 1.91 V/cell for discharge times >10 h; 1.80 V/cell for 1 h),

deep discharges of more than 80 % DOD have to be avoided Unlimited, the minimal charge current has to be $1.5 \text{ A}/100 \text{ Ah C}_{10}$

Initial charge current (I or bulk phase)

I or bulk phase) Charge voltage at cyclic operation Restricted from 2.30 V to 2.40 V per cell, operating instruction is to be observed

Charge voltage at cyclic operation Restricted from Floating voltage/non cyclic voltage 2.25 V per cell

Adjustment of charge voltage No adjustment necessary if battery temperature is kept between 10 °C and 45 °C

(50 °F and 113 °F) in the monthly average, $\Delta U/\Delta T = -0.003$ V/cell per K below 10 °C

(50 °F)


Recharge to 100 % Within a period of 1 up to 4 weeks Battery temperature -20 °C to 45 °C (-4 °F to 113 °F),

recommended temperature range 10 °C to 30 °C (50 °F to 86 °F)

Self-discharge Approx. 2 % per month at 20 °C (68 °F)

IEC 61427 cycles 2,100 (A+B) at 40 °C (104 °F) IEC 60896-21 cycles >1,500 at 20 °C (68 °F)

8. Number of cycles as function of Depth of discharge



9. Transport

Batteries are not subject to ADR (road transport), if the conditions of Special

Provisions 598 and 238 (Chapter 3.3) are observed.

BAE cells/batteries are conform to the IMDG-Code, therefore these products are

no dangerous goods on sea transport.

10. Standards

Germany

Test standards IEC 60896-21, IEC 61427

Safety standard, ventilation IEC 62485-2

BAE Batterien GmbH Wilhelminenhofstraße 69/70 12459 Berlin

Tel.: +49 (0)30 53001-661 Fax: +49 (0)30 53001-667 E-Mail: info@bae-berlin.de www.bae-berlin.de

